

BARE COPPER TINNED

DESCRIPTION:

Solid soft tinned copper wires are used primarily in applications involving current flow, corrosion resistance, or the need to solder the wire to some component. The addition of a tin coating facilitates the soldering process with only a small price differential over bare copper. A tin coating is also desirable in applications where operating temperatures exceed 100°C up to 150°C. At such temperatures the corrosion resistance of bare copper declines and the tin coating acts to protect the surface of the bare copper. The standard minimum thickness of tin coating is 40 micro-inches.

STANDARDS AND SPECIFICATIONS:

- ASTM B33-81
- Bare conductor prior to coating meets ASTM B-1-81, B2-82, or B3-74
- ARRA 2009 Section 1605
"Buy American" Compliant

Conductor			Overall Diameter Inches			Max Resistance OHM/MFT 68°F	Bare WT./MFT
Size (AWG)	Stranding	Individual Strand Size	Nominal	Minimum	Maximum		
2	Solid	0.2576	0.2576	0.2550	0.2653	0.1641	200.9
2/0	19	0.0837	0.4180	0.4138	0.4305	0.043	410.9
4/0	19	0.1147	0.5280	0.5227	0.5438	0.0524	653.3



830 South West Street / Sikeston, MO 63801
800.325.8050 / F: 800.622.3355